

For best results **DRYLOK Extreme** should be well stirred and sprayed at room temperature (70 °F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Use Graco Ult 1095 (1 GPM) or larger Graco electric airless pump. For gas engine use Graco GMAX 3900 (1 GPM) or larger Graco Gas powered unit.

Either unit must have first 50' section of 3/8" x 50' airless hose, connecting to second section a 1/4" x 50' airless hose to a Silver Plus Gun using a 0.031 Graco airless tip. Use either a 30 mesh manifold filter or no filter at all.

Airless pressure must be 3000 psi.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.

Graco HTX 2030 Texture Unit (Gas powered) with HTX Block Gun using a 6MM tip and 50 ft HTX Hose. Use an external 8 hp compressor unit at high flow low idle. Number 3 flow setting. Wet hose then remove all water from fluid line and pump before loading material in to system.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.