



PRODUCT DATA SHEET

DRYLOK® FAST PLUG

DESCRIPTION

DRYLOK Fast Plug is a quick setting hydraulic cement. It sets in 3-5 minutes to stop active leaks, even under pressure, in masonry, seals open joints and even very large cracks in masonry walls. Anchors metal to concrete. Ideal for sealing floor and wall joints and settlement cracks in masonry walls and swimming pools.

APPLICATION

For Active Leaks (the presence of flowing water through a break in the surface): Mix appropriate amount of Fast Plug. In approximately 2 1/2 - 3 minutes, the mixture will become warm to the touch which indicates it is commencing to set. At this time force Fast Plug into the opening with the palm of the hand. Hold in place 3-5 minutes, assuring a complete set and sufficient bond to stop the flow of water. The patched area may be smoothed and trimmed to the surrounding area in approximately 5 minutes. Fast Plug may be painted when set with DRYLOK Masonry Waterproof, Latex Base DRYLOK Masonry Waterproof, DRYLOK Powdered Masonry Waterproof, DRYLOK Concrete Floor Paint or DRYLOK Cement Paint.

For Inactive Leaks, Patching, Anchoring: Thoroughly soak the area. Apply with knife or trowel, smoothing the patch even with the surface. When anchoring, chisel or drill hole in masonry surface slightly larger than item to be anchored. Make certain mixed Fast Plug is tamped firmly into hole and around metal part.

LIMITATION

Mix only enough for immediate use, because DRYLOK Fast Plug sets in 3-5 minutes. Cannot be reworked once it has set.

COVERAGE

One pound of DRYLOK Fast Plug mixed according to directions with water will produce approximately 12 cubic inches of patching material.

INSTALLATION

The area to be patched should be cleaned thoroughly by wire brushing, scraping or any other effective process. Cracks should be chiseled out to the shape of an inverted "V" (the point at the surface).

MIXING

DRYLOK Fast Plug and clean mixing water should be at room temperature prior to mixing. Mix 3 parts Fast Plug and 1 part water thoroughly to a putty or heavy troweling consistency. This mixture will set in 3-5 minutes. The use of colder water or material will retard the setting time. Mix only enough for immediate use due to the quick setting time. DRYLOK Fast Plug cannot be reworked once it has set. In cold weather, use warm (90°F.) water for mixing; also soak surface with warm water before application.

TECHNICAL DATA

DRYLOK Fast Plug is a specially formulated powder material that contains Portland cement. Product is alkaline on contact with water. Use paddle for mixing to avoid contact with skin. For sensitive skin, wear rubber or other protective gloves.

Appearance: Gray-Tan Powder
Compressive strength of cured material at:

1 HOUR	311 PSI
3 HOURS	365 PSI
8 HOURS	396 PSI
24 HOURS	2650 PSI
7 Days	3050 PSI
28 Days	11975 PSI

AVAILABILITY

DRYLOK Fast Plug is available through local dealers and distributors. In areas not serviced, contact United Gilsonite Laboratories for details.

LR 9/11

PRODUCT DATA
DRYLOK FAST PLUG



United Gilsonite Laboratories:
Corporate Headquarters
1396 Jefferson Avenue
Dunmore, PA 18509
Tel: 1-800-272-3235
www.ugl.com