



PRODUCT DATA SHEET

DRYLOK® MASONRY TREATMENT

DESCRIPTION

DRYLOK Masonry Treatment is a waterborne acrylic product that protects interior and exterior masonry surfaces from corrosive liquids and weathering. DRYLOK Masonry Treatment can also be used as a primer for latex paint.

As A Sealer: DRYLOK Masonry Treatment penetrates deep to seal and protect masonry against acids, alkalis, household cleaners, gasoline, oil and salt. It also seals against dusting and retards spalling (surface cracking and pockmarking) and weathering. Treats chalking masonry paint, porous asbestos siding, sandblasted masonry and powdering mortar, before applying a latex paint.

As a Concrete Curing Membrane: When applied to freshly poured concrete, after the surface has set and excess water has been removed, DRYLOK Masonry Treatment will control water evaporation resulting in maximum concrete hardness. Allow 28 days before applying subsequent coatings.

SURFACE PREP

Remove all dirt, wax, dust, mildew, and loose or scaling material with a scraper, wire brush or stiff bristle brush. Grease and oil should be removed by scrubbing with DRYLOK Concrete Cleaner & Degreaser or a heavy duty detergent in warm water. Rinse surface with clean water. Efflorescence (saltlike deposits) should be removed with DRYLOK Etch (powder or liquid) or muriatic acid according to manufacturer's directions, then rinsed thoroughly with clean water. Etching solutions

allowed to dry on masonry surfaces prevent proper curing of the finish coat. This may result in the masonry treatment appearing milky when dry. Cracks and holes should be filled with DRYLOK Concrete Patch.

APPLICATION

Apply only when surface temperature is above 50°F. Apply full strength with brush, pad applicator, garden sprayer or squeegee. Spread evenly - do not allow puddles or a heavy surface film to occur.

One coat is generally sufficient for most surfaces. If a second coat is required (extremely porous surfaces) allow 6 hours between coats. Additional coats will cause surface to be slippery when wet.

On light-colored surfaces, some darkening may take place; test in an inconspicuous area to be sure darkening does not occur. May be applied to surfaces previously coated with a similar treatment. For best results, test a small area for proper adhesion prior to coating entire surface. If a sheen is desired we recommend DRYLOK WetLook High Gloss Sealer.

THINNING

When applied over flagstone, slate, terrazzo or dense, smooth concrete, thin DRYLOK Masonry Treatment with equal parts of clean, lukewarm water. In addition, light colored concrete may darken unevenly due to variations in porosity. To minimize color variations, thin with water 1 to 1 and test on small area to see final effect.

USED AS A PRIMER

DRYLOK Masonry Treatment will solidify the surface for painting when applied over powdery surfaces such as chalking masonry paint, porous asbestos siding, sand blasted masonry and powdering mortar. It is also ideal for use as a PRIMER-SEALER under latex, alkyd or polyurethane concrete floor paints or carpeting. For self adhesive floor tiles, check with tile manufacturer for adhesion compatibility.

DRYING

Allow 6 hours before subjecting to light foot traffic and 24 hours before subjecting to heavy traffic. During periods of high humidity and/or cool temperatures, allow 24 hours before subjecting to light foot traffic.

COVERAGE

One gallon of DRYLOK Masonry Treatment will cover up to 400 square feet depending on surface porosity.

CLEAN-UP

Clean tools with soap and water.

MAINTENANCE

None required. Because DRYLOK Masonry Treatment prevents the penetration of dirt, moisture, etc., coated surfaces are easy to clean.

DRYLOK® MASONRY TREATMENT

TECHNICAL DATA

Non-Volatile by Weight - 15.0%
Non-Volatile by Volume - 12.5%
Wt./Gal. - 8.4 lbs.
pH - 8.9
Viscosity - 11 Sec. Ford #4 Cup @ 75°F.

SPECIFICATION

DRYLOK Masonry Treatment meets California's 250-grams-per-liter VOC level for architectural specialty coatings classified as general sealers.

SPECIFICATION

DRYLOK Masonry Treatment is not recommended as a waterproofer. For masonry walls subjected to hydrostatic pressure, use DRYLOK Masonry Waterproofing. Do not use over silicone treated surfaces.

AVAILABILITY

DRYLOK Masonry Treatment is available in gallon and five gallon containers. It is sold in hardware and paint stores, lumberyards and home centers.

UGL makes a complete line of masonry products including DRYLOK Masonry Waterproofing in powdered, Oil and Latex Base Formulas. Also included in the DRYLOK line are DRYLOK Etch, DRYLOK Concrete Cleaner and Degreaser, DRYLOK Fast Plug, DRYLOK Masonry Crack Filler, DRYLOK Latex Concrete Patch, DRYLOK Concrete Protector, DRYLOK Latex Concrete Floor Paint, DRYLOK Latex Bonding Agent and DRYLOK Water-Base 5% Silicone.

