

For best results Designer DRYLOK should be well stirred and sprayed at room temperature (60°F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Graco HTX 2030 Texture Unit (Gas powered) with HTX Hand Gun using a 6MM tip and 50 ft HTX Hose. Use an external 8 hp compressor unit at high flow low idle. Wet hose then remove all water from fluid line and pump before loading material in to system.

Graco RTX 1500 Texture Unit (Electric powered) with RTX hand gun using an 8MM tip and 25 ft RTX Hose. Use External compressor at 55 psi. Wet hose then remove all water from fluid line and pump before loading material in to system.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.

United Gilsonite Laboratories does not recommend air spray application for this product.