



PRODUCT DATA SHEET

LATEX BASE NUDECK® ROOF CEMENT

DESCRIPTION

NUDECK Roof Cement is a latex base construction-grade elastomeric caulking sealant designed for cementing and waterproofing chimney and dormer flashings, valley joints and all types of roof seams. NUDECK may be used on WET OR DRY surfaces and retains its elasticity and water resistance for years. The elastomeric and adhesive properties of NUDECK produce a tough and flexible sealant designed to resist variations in temperature and weather. VOC compliant and odor free. NUDECK is ideal sealant for most roofing and waterproofing projects.

NUDECK ROOF CEMENT is ideal for sealing leaks in and around asphalt built-up-roofs, shingles, joints, chimney cracks, skylights, vents, down-spouts, gutters and leaks on slate or metal roofs. NUDECK may also be used to improve wind resistance on low slope shingle roofs.

SURFACE PREP

Do not apply when rain is imminent. All surfaces to be caulked should be clean and free from oil, grease, rust, dirt, mud, slag, paint and loose particles (such as stones, gravel or pebbles) before applying NUDECK.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

May be applied to wet or dry surfaces when air and surface temperatures are above 50°F (10°C). If applied to a wet surface all puddles of water must be removed. NUDECK normally cures in 12 hours. Application under conditions of extreme dampness or high humidity prolongs drying, rendering sealant vulnerable to driving rain. Cut end of plastic spout at 45° angle to desired bead size. NUDECK should be applied directly over the crack using a standard open cradle caulking gun. Use a trowel to smooth the caulk onto the surface. An application rate of 1/4" x 1/4" bead of caulk will yield approximately 25 linear feet per 10.1 oz. caulking cartridge. Coverage rate may vary depending on desired thickness and surface to be caulked. NUDECK must be dry before exposure to water.

CAUTION

Avoid prolonged contact with skin. Close container after each use. KEEP OUT OF REACH OF CHILDREN. KEEP FROM FREEZING.

TECHNICAL DATA

Percent Non-Volatile by Weight: 54%
Weight Per Gallon: 1.41 lbs.
VOC Content - 25% g/L
Petroleum Asphalt - 40-50%
Polymer - 2 to 7%

AVAILABILITY

NUDECK Roof Cement comes in a 10.1 oz. cartridge. It is available at hardware stores, home centers, paint stores, and lumberyards.

PRODUCT DATA
LATEX BASE NUDECK ROOF CEMENT

LR 1/08



United Gilsonite Laboratories:
Corporate Headquarters
1396 Jefferson Avenue
Dunmore, PA 18509
Tel: 1-800-272-3235
www.ugl.com