

Revision #4 May 2011  
(Supersedes Revision #3 March 2005)

## DRYLOK CONCRETE FLOOR PAINT TINTING FORMULATION

MATCHING: DRYLOK CONCRETE FLOOR PAINT COLORS

SYSTEM: PPG USING 48 INCREMENTS PER FLUID OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

### COLORANTS

- B – Lamp Black
- C – Yellow Oxide
- D – Thalo Green
- E – Thalo Blue
- F – Red Iron Oxide
- G – Durable Yellow
- L – Raw Umber
- M – Durable Red
- V – Violet
- W – White

## DRYLOK CONCRETE FLOOR PAINT COLORS – PPG

### BAMBOO BEIGE

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow oxide	0	40			
			F – Red Iron Oxide	0	4			
			L – Raw Umber	2	38			
			W – White	5	24			

### CARAMEL

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow oxide	2	12			
			F – Red Iron Oxide	0	18			
			E – Thalo Blue	0	14			
			W – White	6	0			

### DEEP CHARCOAL

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	12			
			D – Thalo Green	0	2			
			L – Raw Umber	0	28			
			W – White	1	0			

### DOVER GRAY

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	16			
			C – Yellow oxide	0	22			
			W – White	7	8			

### GEORGETOWN GRAY

#### DARK TINT BASEBASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	2			
			C – Yellow oxide	0	36			
			E – Thalo Blue	1	8			
			W – White	7	0			

## DRYLOK CONCRETE FLOOR PAINT COLORS – PPG

### GULL

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	40			
			C – Yellow oxide	0	10			
			W – White	8	0			

### PERSIAN RED

#### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	24			
			F – Red Iron Oxide	1	42			
			M – Durable Red	7	14			
			W – White	0	8			

### PLATINUM

#### WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	16			
			C – Yellow oxide	0	30			
			M – Durable Red	0	8			

### SANDSTONE

#### WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	14			
			C – Yellow oxide	0	42			
			F – Red Iron Oxide	0	4			

### SOFT GRAY

#### WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	10			
			C – Yellow oxide	0	22			

## DRYLOK CONCRETE FLOOR PAINT COLORS – PPG

### SPRUCE

### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow oxide	1	24			
			D – Thalo Green	2	32			
			L – Raw Umber	4	32			
			W – White	3	8			

### TERRA COTTA

### DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	22			
			F – Red Iron Oxide	2	34			
			M – Durable Red	1	24			
			W – White	4	12			

### BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

### BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

### BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s