

Revision #4 May 2011
(Supersedes Revision #3 March 2005)

DRYLOK CONCRETE FLOOR PAINT TINTING FORMULATION

MATCHING: DRYLOK CONCRETE FLOOR PAINT COLORS

SYSTEM: **TRUE VALUE** USING 48 INCREMENTS PER FLUID OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

AX – Exterior Yellow
B – Lamp Black
C – Yellow Oxide
D – Thalo Green
E – Thalo Blue
F – Red Iron Oxide
I – Brown Iron Oxide
KX – Titanium Dioxide
L – Raw Umber
R – Exterior Red

DRYLOK CONCRETE FLOOR PAINT COLORS – TRUE VALUE

BAMBOO BEIGE

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	28			
			C – Yellow Oxide	0	40			
			F – Red Iron Oxide	0	6			
			KX – Titanium Dioxide	3	0			

CARAMEL

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	2	12			
			F – Red Iron Oxide	0	18			
			E – Thalo Blue	0	14			
			KX – Titanium Dioxide	6	0			

DEEP CHARCOAL

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	12			
			D – Thalo Green	0	2			
			L – Raw Umber	0	28			
			KX – Titanium Dioxide	1	0			

DOVER GRAY

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	36			
			C – Yellow Oxide	0	8			
			KX – Titanium Dioxide	2	24			

GEORGETOWN GRAY

DARK TINT BASEBASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	2			
			C – Yellow Oxide	0	36			
			E – Thalo Blue	1	8			
			KX – Titanium Dioxide	7	0			

DRYLOK CONCRETE FLOOR PAINT COLORS – TRUE VALUE

GULL

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	24			
			C – Yellow Oxide	0	4			
			KX – Titanium Dioxide	2	28			

PERSIAN RED

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	8			
			F – Red Iron Oxide	1	24			
			L – Raw Umber	1	32			
			R – Exterior Red	2	32			
			KX – Titanium Dioxide	0	10			

PLATINUM

WHITE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	12			
			C – Yellow Oxide	0	24			
			L – Raw Umber	1	20			

SANDSTONE

WHITE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	36			
			L – Raw Umber	1	24			

SOFT GRAY

WHITE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	24			
			C – Yellow Oxide	0	24			

DRYLOK CONCRETE FLOOR PAINT COLORS – TRUE VALUE

SPRUCE

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	1	24			
			D – Thalo Green	2	32			
			L – Raw Umber	4	32			
			KX – Titanium Dioxide	3	8			

TERRA COTTA

DARK TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	4			
			F – Red Iron Oxide	1	8			
			L – Raw Umber	1	12			
			R – Exterior Red	1	6			
			KX – Titanium Dioxide	2	16			

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s