

APRIL 2015

DRYLOK CONCRETE STAIN AND TONER TINTING FORMULATION

MATCHING: DRYLOK CONCRETE STAIN AND TONER COLORS

SYSTEM: **BASF PURE OPTIONS** USING 48 INCREMENTS PER FLUID OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

- B – Lamp Black
- C – Yellow Oxide
- DU – Phthalo Green
- EU – Phthalo Blue
- F – Red Oxide
- KX – White
- L – Raw Umber
- R – Organic Red

DRYLOK CONCRETE STAIN AND TONER– BASF PURE OPTIONS

AUTUMN SUN

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	6			
			F – Red Oxide	0	35			
			L – Raw Umber	0	20			
			R – Organic Red	0	18			
			KX – White	0	36			

BATTLESHIP GRAY

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	24			
			C – Yellow Oxide	0	6			
			KX – White	1	40			

BLUE STONE

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	34			
			C – Yellow Oxide	0	16			
			EU – Phthalo Blue	0	10			
			KX – White	2	0			

CONCRETE GRAY

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	20			
			C – Yellow Oxide	0	10			
			KX – White	4	24			

CREAM

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	12			
			L – Raw Umber	0	16			
			KX – White	5	12			

DRYLOK CONCRETE STAIN AND TONER – BASF PURE OPTIONS

DESERT STONE

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	14			
			C – Yellow Oxide	0	14			
			F – Red Oxide	0	2 ½			
			KX – White	0	40			

DUSTY CHARCOAL

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	42			
			L – Raw Umber	0	10			
			KX – White	0	16			

FOREST GREEN

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	28			
			DU – Phthalo Green	0	35			
			L – Raw Umber	1	26			
			KX – White	1	2			

MAPLE BROWN

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	12			
			C – Yellow Oxide	0	16			
			F – Red Oxide	0	7			
			L – Raw Umber	0	12			
			KX – White	0	44			

MYSTIC GRAY

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	24			
			C – Yellow Oxide	0	4			
			KX – White	1	16			

DRYLOK CONCRETE STAIN AND TONER – BASF PURE OPTIONS

PRUSSIAN BLUE

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	10			
			C – Yellow Oxide	0	4			
			EU – Phthalo Blue	0	6			
			KX – White	1	4			

PUEBLO CLAY

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	24			
			F – Red Oxide	0	7			
			EU – Phthalo Blue	0	3			
			KX – White	1	16			

SAGE

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	2			
			C – Yellow Oxide	0	16			
			EU – Phthalo Blue	0	4			
			L – Raw Umber	0	4			
			KX – White	2	4			

SOFT BRICK

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	20			
			F – Red Oxide	1	31			
			L – Raw Umber	0	40			
			R – Organic Red	1	16			

SOFT PLATINUM

245 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	4			
			C – Yellow Oxide	0	4			
			L – Raw Umber	0	16			
			KX – White	3	36			