

APRIL 2015

DRYLOK LATEX WATERPROOFER FORMULATION

MATCHING: DRYLOK LATEX WATERPROOFER COLORS

SYSTEM: **BASF PURE OPTIONS** USING 48 INCREMENTS PER FLUID OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

AX - Exterior Yellow
B - Lamp Black
C - Yellow Oxide
DU - Thalo Green
EU - Thalo Blue
F- Red Iron Oxide
I – Brown Iron Oxide
KX - Titanium Dioxide
L - Raw Umber
R – Exterior Red

DRYLOK LATEX COLORS – BASF PURE OPTIONS

BEIGE

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	½	B – Lamp Black	0	2 ½
			C – Yellow Oxide	0	3	C – Yellow Oxide	0	15
			F – Red Iron Oxide	0	½	F – Red Iron Oxide	0	2 ½
			L – Raw Umber	0	10	L – Raw Umber	1	2

BLUE

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			EU – Thalo Blue	0	8	EU – Thalo Blue	0	40

BUTTERCUP

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			AX – Exterior Yellow	0	8	AX – Exterior Yellow	0	40

GRAY

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	13	B – Lamp Black	1	17
			C – Yellow Oxide	0	3	C – Yellow Oxide	0	15

MINT GREEN

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			AX – Exterior Yellow	0	½	AX/AXX – Exterior Yellow	0	2 ½
			DU – Thalo Green	0	1 ½	D – Thalo Green	0	7 ½

DRYLOK LATEX COLORS – BASF PURE OPTIONS

PLATINUM

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	4	B – Lamp Black	0	20

SAND

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	4	C – Yellow Oxide	0	20
			L – Raw Umber	0	2	L – Raw Umber	0	10

SLATE BLUE

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			EU – Thalo Blue	0	1 ½	EU – Thalo Blue	0	7 ½
			R – Exterior Red	0	½	R – Exterior Red	0	2 ½

SOFT PINK

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	2	C – Yellow Oxide	0	10
			R – Exterior Red	0	4	R – Exterior Red	0	20

WHITE BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s