

February 2016

50 g/L DRYLOK® E1 LATEX 1-PART EPOXY CONCRETE FLOOR PAINT
TINTING FORMULATION

MATCHING: 50 g/L DRYLOK® E1 LATEX 1-PART EPOXY CONCRETE FLOOR
PAINT

SYSTEM: **VALSPAR NOVOCOLOR II** USING 48 INCREMENTS PER FLUID
OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 48, lists the number(s) of fractions, 48ths, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

- B – Lamp Black
- C – Yellow Oxide
- D – Phthalo Green
- E – Phthalo Blue
- F – Red Oxide
- KX – White
- L – Raw Umber
- S – Fast Red

ARCTIC WHITE

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			KX – White	0	8			

CHESTNUT

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	4			
			C – Yellow Oxide	3	0			
			F – Red Oxide	1	8			
			KX – White	1	16			

COBALT BLUE

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	32			
			E – Phthalo Blue	3	24			
			S – Fast Red	1	12			

DARK GRAY

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	2	12			
			C – Yellow Oxide	1	15			
			S – Fast Red	0	8			

GRAY

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	26			
			C – Yellow Oxide	0	24.5			
			F – Red Oxide	0	1			

50 g/L DRYLOK® E1 LATEX 1-PART EPOXY CONCRETE FLOOR PAINT – VALSPAR NOVOCOLOR II

HARVEST BROWN

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	1	13			
			F – Red Oxide	0	4			
			L – Raw Umber	1	41			

NATURAL SAND

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			C – Yellow Oxide	0	11			
			F – Red Oxide	0	0.5			
			L – Raw Umber	0	19			

PLATINUM

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	22			
			C – Yellow Oxide	0	6			

SAGE

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	30			
			C – Yellow Oxide	3	28			
			D – Phthalo Green	1	3			

SKY BLUE

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	1	47			
			C – Yellow Oxide	0	3			
			D – Phthalo Green	1	30			

STONE BLUE

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	4	8			
			C – Yellow Oxide	1	23			
			D – Phthalo Green	1	30			

TERRA COTTA

284 TINT BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s
			B – Lamp Black	0	26			
			C – Yellow Oxide	0	8			
			F – Red Oxide	6	24			
			S – Fast Red	0	24			

COLOR NAME & NUMBER

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

COLOR NAME & NUMBER

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s

COLOR NAME & NUMBER

BASE

Quart Formula			Gallon Formula			Five Gallon Formula		
Colorant	OZS.	48s	Colorant	OZS.	48s	Colorant	OZS.	48s